







AJL VISC
AJL CELL



The future of vision

AJL VISC – AJL CELL Viscoelastic Solutions

Brand name	AJL VISC			AJL CELL
Reference	AJL VISC 1.4%	AJL VISC 2%	AJL VISC 3%	AJL CELL 2%
Description	Non-absorbable viscoelastic solution, highly purified and non-inflammatory, isotonic, sterile and non-pyrogenic, for intraocular injection.			
Properties	<ul style="list-style-type: none"> • High endothelium protection. • Viscoelastic solutions are used to maintain the endo-ocular space and the integrity of anterior segment. • Excellent rheological properties. • Viscoelastic solutions offer excellent visibility of the treated area. • Easy to remove from anterior chamber. 			
Composition / Molecular Weight (MW)	Sodium Hyaluronate/ MW: 2.400.000 Da			Hydroxypropyl Methylcellulose (HPMC)/ MW: 92.000 Da
Viscosity (1 S ⁻¹ 25°C)	15 000-20 000 mPa-s	40 000-60 000 mPa-s	160 000-200 000 mPa-s	2 000-4 000 mPa-s
pH	7.0-7.5	7.0-7.5	7.0-7.5	7.0-7.5
Osmolarity	250-350 mOsmol/l	250-350 mOsmol/l	250-350 mOsmol/l	250-350 mOsmol/l
Volume	1 ml	1 ml	1 ml	2 ml
Supply	Sterile, single unit. Prefilled glass syringe of 1 ml. Luer lock 27G cannula. Blue backstop. 	Sterile, single unit. Prefilled glass syringe of 1 ml. Luer lock 27G cannula. Pink backstop. 	Sterile, single unit. Prefilled glass syringe of 1 ml. Luer lock 25G cannula. Green backstop. 	Sterile, single unit. Prefilled glass syringe of 2 ml. Luer lock 27G cannula. Transparent backstop. 
Sterilization method	Steam.			
Shelf-life	3 years			

CE 0434

REV: 03